

TRX-50 General Purpose Wax/Resin

RIBBON PROPERTIES

Ink Color	Black
Base Film Thickness	4.5 ± 0.3 μ
Ink Thickness	3.3 ± 0.2 μ
Total Thickness	7.8 ± 0.5 μ
Transfer Temperature	185°F / 85°C

RECOMMENDED SUBSTRATES

TAG / PAPER	SYNTHETICS	SPECIALTY MATERIALS
Uncoated Tag	Polypropylene	Tyvek®
Coated Tag	Polyethylene	Tyvek Brillion®
Gloss Sheets	Polystyrene	Valeron®
	Polyolefin	
	Vinyl (Topcoat)	

PRODUCT FEATURES

- Smoothcoat® Backcoat
- FDA Indirect Food Contact
- REACH Compliant
- RoHS Compliant
- Halogen-free

RECOMMENDED APPLICATIONS

AUTOMOTIVE



CHEMICALS



ELECTRONICS



FOOD & BEVERAGE



INVENTORY & LOGISTICS



OUTDOOR



PHARMACEUTICAL



RETAIL



UL / cUL LABELING REFERENCES

FLEXcon:

PGJI2.MH16635

The information on this datasheet was obtained in DNP laboratories. Measured values may vary slightly when tested in a different environment. Information contained within this document is subject to change without notification.

DNP Imagingcomm America Corporation

1001 Technology Drive | Mount Pleasant, PA 15666

Phone: 1.888.569.7222 | Fax: 1.800.676.7669

Email: info@dnp.imagingcomm.com | Web: am.dnpribbons.com



DNP